

STANDARD PRODUKTE

DRUCKBARE PRODUKTE

		STANDARD PRODUKTE															DRUCKBARE PRODUKTE																				
		POLI-FLEX® PREMIUM	POLI-FLEX® BLOCKOUT SOFT	POLI-FLEX® NYLON	POLI-FLEX® STRETCH	POLI-FLEX® SPORT	POLI-FLEX® TURBO	TUBITHERM	TUBITHERM NEON COLOURS	POLI-FLEX® 5001 BLOCKOUT WHITE	POLI-FLEX® IMAGE REFLEX SILVER 4781 / REFLEX ECO 4782	POLI-FLEX® 4214 / 4215 DIMENSION	POLI-FLEX® IMAGE BRILLANT 421 / 431	POLI-FLEX® IMAGE LUMINOUS	POLI-FLEX® PEARL GLITTER	POLI-FLEX® IMAGE PAINT / GLOSSY	POLI-FLEX® IMAGE / STARFLEX	POLI-FLEX® IMAGE 4222 - 4275	TURBO PRINT 4036 MATT	ULTIMATE PRINT SOFT 4030/4032 MATT/4031 GLOSS	ULTIMATE PRINT MATT 4025	ULTIMATE PRINT SUPERSOFT 4033 MATT	TURBO PRINT TRANSPARENT SOFT 4034 MATT	POLI-FLEX® 4010-S BLOCKOUT	POLI-FLEX® 4015 / 4016	POLI-FLEX® 4600 / 4605	POLI-FLEX® 4655	POLI-FLEX® 4625	POLI-FLEX® 4665 METALLIC	SUBLI-FLOCK® 4675	SOLVENT-FLOCK 5901 / TUBITHERM PES						
TRANSFEREMPFEHLUNG	Temperatur (°C)	160	130	150	160	130	Standard 160 150 130	Nylon* 150	160	160	160	160	150	160	160	160	160	160	160	160	160	160	150	130	160	160	160	160	160	160	160	160	160				
	Druck (bar)	2,5 - 3,0	2,5 - 3,0	2,0	2,5 - 3,0	2,5 - 3,0	2,5 - 3,0	2,0	2,0	2,0	2,0	2,5 - 3,0	2	3,0	2,5 - 3,0	2,5 - 3,0	2,5 - 3,0	2,5 - 3,0	2,5 - 3,0	2,5 - 3,0	2,5 - 3,0	2,5 - 3,0	2,0	2,5 - 3,0	2,5 - 3,0	2,5 - 3,0	2,5 - 3,0	2,5 - 3,0	2,5 - 3,0	2,5 - 3,0	2,5 - 3,0	2,5 - 3,0					
	Zeit (sec.)	15	5	Vorpressen 4 zweites pressen 10	15	10	3 4 5	5 + 5 + 10*	15	15	15	15	Vorpressen 4 zweites Pressen 10	25	15	15	15	15	15	15	15	15	3 4 5	5 + 5 + 10*	15	15	15	15	Vorpressen 4 zweites pressen 10	5	15	15	15	15	15	15	15
	Abzug (Warm= W / Kalt= K)	W	W	W	W	W	W & K	W & K	W	K	W	W	W	K	K	K	K	W	W	W	K	W	W	W	W	W	W	W	W	W	W	W	W	W	W		
WASCHEMPFEHLUNG	Washbeständigkeit (°C)	80	60	40	80	40	60	40	60	40	40	60	40	60	40	nur Handwäsche	60	60	60	60	40	60	60	60	60	60	60	60	60	40	90	60	40	40			
	Wäschetrockner	●			●	●	●**		●	●		●			●	●	●	●	●	●	●	●	●	●		●	●	●	●	●	●	●	●	●	●		
	Chemische Reinigung	●	●		●	●	●								●		●																				

*POLI-FLEX® TURBO & TURBO PRINT
 • Vorpressen 5 sek.
 • Pressen auf Nylon 5 sek.
 • nach Entfernen des PET-Liners 10 sek. pressen

** POLI-FLEX® TURBO TURBO PRINT gewerbliche Wäschetrockner bis zu 100°C